

**APPENDIX
ASTM F 2412-05
ELECTRICAL SHOCK RESISTANCE**

PRODUCT DESCRIPTION: Slipp-R

CONDITIONING: In accordance with ASTM D1776 at a temperature $21^{\circ}\text{C} \pm 3^{\circ}\text{C}$ ($70^{\circ}\text{F} \pm 5^{\circ}\text{F}$) and a relative humidity of $65\% \pm 5\%$ until equilibrium is reached or for at least 24 hours, whichever is shorter.

SAMPLE TYPE: Rubber Steel Toe Overshoe

TYPE OF TEST: a-c

PERSCRIBED PROOF TEST VOLTAGE: 14,000

LENGTH OF PROOF TEST: 60 sec

SAMPLE NO.	CURRENT LEAKAGE (mA)
1	0.67