

**ASTM D 1630-04
ABRASION RESISTANCE****PRODUCT DESCRIPTION:** Slipp-R**CONDITIONING:** At a temperature $21^{\circ}\text{C} \pm 3^{\circ}\text{C}$ ($70^{\circ}\text{F} \pm 5^{\circ}\text{F}$) and a relative humidity of $65\% \pm 5\%$ until equilibrium is reached or for at least 24 hours, whichever is shorter.**SAMPLE TYPE:** Rubber Steel Toe Overshoe

SAMPLE NO.	1	2	3	AVG.
CYCLES TO ABRAIDE	367	370	553	430
NBS ABRASION NO.	65	71	58	65